



Renewable Lubricants, Inc.

476 Griggy Rd., P.O. Box 474

Hartville, Ohio 44632-0474

Voice: 330.877.9982 Fax 330.877.2266

Web: www.renewablelube.com

Bio-Ultimax™ 1200LT

Hydraulic Fluids

(ISO 5, 10, 15, 22, 32, 46)



"Biobased Lubricants that Perform Like Synthetics"

Bio-Ultimax™ 1200LT (Low Temperature) Hydraulic Fluids are ultimately biodegradable¹, biosynthetic formulas that were designed specifically to replace and outperform mineral oil based hydraulic fluids for environmentally sensitive and/or cold temperature areas. These patented biobased hydraulic fluids are formulated to perform in high and low-pressure hydraulic systems that require Anti-Wear (AW), anti-rust, anti-oxidation, anti-foam, and demulsibility properties. They are highly inhibited against moisture and rusting in both fresh and sea water and pass both A and B Sequences of the ASTM D-665 Turbine Oil Rust Test. Incorporating the super high viscosity index of the Stabilized* HOBS into the formula, gives multi-grade synthetic base oil performance by boosting the viscosity index (VI) past synthetic levels (energy conserving formulas). This super high viscosity index naturally improves the thermal shear stability of the formula and increases load capacity. They provide additional fluid value at the higher temperatures, which is a performance benefit over lower VI products of the same ISO viscosity. The HOBS's extremely low volatility increases the flash and fire safety features in the formula compared to petroleum formulations with the same viscosity ranges. They are formulated to provide seal conditioning for longer seal life and to reduce oil leakage from the system. They are compatible with the same seals, filters, materials and components that are designed to operate on petroleum oil-based formulations. An environmentally friendly, zinc-free additive system has also been developed that meets or exceeds high pressure pump requirements.

Bio-Ultimax™ Hydraulic Fluids have a long-term history of proven performance with over 15 years of successfully being used in a wide variety of stationary and mobile hydraulic equipment. These patented super high VI fluids have performed successfully in hydraulic systems up to 10,000 psi and in systems with ultra-fine filtration. They are designed for use in hydraulic vane, piston, and gear-type pumps that require DIN 51524 Part 2 and 3 (HLP/HVLP), Parker-Denison HF-O/T6H20C, HF-1, HF-2, Eaton-Vickers M-2950-S (35VQ-25) and I-286-S (V-104C), Rexroth, Sauer-Sundstrand, GM (LS-2), US Steel 126, 136, and 127. They also meet the requirements for ashless GL-1, GL-2, GL-3 and AGMA Non-EP gear oils in reduction units and gear sets, where they meet the viscosity ranges. They have shown to have exceptional anti-wear performance in ASTM D-4172 Four Ball Wear Tests. **Very little wear was encountered in the field studies and in accelerated pump tests using biobased formulations in Denison T-5D, Vickers 20VQ, 35VQ-25 (M-2950-S), and V-104C (ASTM D-2882), Vickers I-286-S pump stand tests at pressures and temperatures ranging from 2000 to 3000 psi and from 150⁰ to 210⁰ F.** Their anti-wear performance **exceeds the requirements** for GM (LS-2), US Steel 126, 136 and 127, load stage 10 in the FZG (DIN 51354), and DIN 51524 Part 2 and 3 requirements for low viscosity hydraulic and turbine oils. They may be used in reduction gears for cold temperature applications, where the OEM recommends a lighter viscosity or SAE 0W for proper channelling.

Bio-Ultimax™ 1200 LT Hydraulic Fluids are **recommended** for use with Viton fluorocarbon (FKM 2), fluorosilicone, Teflon (PTFE), Polyurethane (AU), polysulfide, Medium to high nitrile rubber (Buna N, >30% acrylonitrile) and Hydrogenated Nitrile Buna Rubber (HNBR). They are **not recommended** for use where neoprene, natural rubber, and styrene-butadiene rubber (SBR, Buna S) seals are used, and ISO grades 5, and 10 provide high seal swell on Low nitrile rubber NBR-L, NBR1 (Buna N, <30% acrylonitrile).

Bio-Ultimax™ 1200 LT Hydraulic Fluids meet the Environmental Protection Agency (EPA) 2013 Vessel General Permit (VGP) guidelines for Environmentally Acceptable Lubricants (EALs), and should be used in hydraulic systems where **LOW TOXICITY, BIODEGRADABILITY** and **NON-BIOACCUMULATION** properties are required. They exceed the acute toxicity (LC-50 / EC-50 >1000 ppm) criteria adopted by the US Fish and Wildlife Service and the US EPA. Because they meet the environmental requirements they can also be used where ISO 15380 (HEES/HETG) Hydraulic Fluids are specified. Bio-Ultimax™ Hydraulic Fluids are **ENVIRONMENTALLY ACCEPTED LUBRICANTS (EALs)** that are formulated from renewable biobased resources. We believe Earth's environmental future rests in the use of renewable materials.

¹Ultimate/Readily Biodegradation Pw1 >60% within 28 days in ASTM D-5864 Aerobic Aquatic Biodegradation of Lubricants

STABILIZED by Renewable Lubricants™ is RLI's trademark on their proprietary and patented anti-oxidant, anti-wear, and cold flow technology. High Oleic Base Stock (HOBS) are agricultural biobased oils. This Stabilized technology allows the HOBS to perform as a high performance formula in high and low temperature applications, reducing oil thickening and deposits. Patented Product: US Patent 6,383,992, US Patent 6,534,454 with additional Pending and Foreign Patents™ Trademark of Renewable Lubricants, Inc. Copyright 1999 Renewable Lubricants, Inc.

Availability F.O.B.: Hartville, Ohio, USA

1 Gallon

5 Gallon Pail

Drum

Totes

Bulk

Bio-Ultimax™ 1200LT Hydraulic Fluids ISO 15, 22, 32, 46

The test data below shows that the Bio-Ultimax™ 1200LT Hydraulic Fluids provide high performance in a wide variety of stationary and transportation equipment, that operate in broad ranges of environmental conditions. In equipment operating outside, wear from poor cold temperature pumpability, surge loads, moisture, and dusty environments are more prominent. Bio-Ultimax™ 1200LT Hydraulic Fluids are formulated to improve performance in equipment that requires excellent anti-wear, rapid water separation, filterability, and cold temperature pumpability as low as -40°C for OW formulations. ISO grades 15 and 22 meet and exceed SAE 0W, ISO 32 meets and exceeds 0W20, and ISO 46 meets and exceeds SAE 0W30 viscosity requirements.

TYPICAL SPECIFICATIONS	METHOD	ISO 5	ISO 10	ISO 15	ISO 22	ISO 32	ISO 46	Spec. Require
Viscosity @ 40°C, cSt	ASTM D-445	4.48	10.65	14.0	21.3	30.9	44.9	Note 1
Viscosity @ 100°C, cSt	ASTM D-445	1.35	3.08	3.9	5.3	7.1	9.8	Note 1
Viscosity @ -20°C, cSt	ASTM D-445	86.68	154.8	225	425	775	1030	Note 1
Viscosity @ -30°C Brookfield	ASTM D-2983	500	900	900	1300	1750	2250	Note 1
Viscosity @ -40°C MRV TP1	ASTM D-4684	2200 cP	2200 cP	2200 cP	3050 cP	6500 cP	17500 cP	0W= <60,000 cP
Viscosity Index	ASTM D-2270	151	160	189	199	204	212	90 (min)
Pour Point	ASTM D-97	-60°C	-60°C	-60°C	-54°C	-50°C	-48°C	Note 1
Flash Point (COC)	ASTM D-92	320°F/160°C	338°F/170°C	365°F/185°C	428°F/220°C	451°F/233°C	462°F/239°C	175-195°C (min)
Hydrolytic Stability, Copper Wt. Loss (mg)	ASTM D-2619	0.0139	0.0139	0.0139	0.0208	0.0208	0.0208	(DIN EN ISO 2592)
Copper Appearance		1B	1B	1B	1B	1B	1B	0.2
Water Layer		3.0	3.0	3.0	3.0	3.0	3.0	Report 4
Foam Sequence I, II, III (10 min)	ASTM D-892	<40/0 Foam	<40/0 Foam	<30/0 Foam	<30/0 Foam	<30/0 Foam	<30/0 Foam	150/0, 80/0, 150/0
Rust Prevention	ASTM D-665	Pass	Pass	Pass	Pass	Pass	Pass	(DIN EN ISO 6247)
Distilled Water		Pass	Pass	Pass	Pass	Pass	Pass	Pass
Syn. Sea Water		Pass	Pass	Pass	Pass	Pass	Pass	Pass
Copper Corrosion Strip 3hr @ 100°C	ASTM D-130	1A	1A	1A	1A	1A	1A	DIN 51524 2(max)
Rotary Bomb Oxidation, (minutes)	ASTM D-2272	450	450	450	450	450	450	USS 120 (min)
Dielectric Strength (KV) (Avg)	ASTM D-877	49	49	49	49	50	45	>35
Oxidation Stability (Pressure Differential Scanning Calorimeter) min	ASTM D-5483 Modified	90 (165°C)	90 (165°C)	90 (165°C)	90 (165°C)	90 (165°C)	90 (165°C)	Note 2
Neutralization Number mg KOH/g	ASTM D-974	<0.4	<0.4	<0.4	<0.4	<0.4	<0.4	1.5 (max)
Swell of Synthetic NBR1 Rubber, % (Avg.)	DIN 53538, Part 1	12.0	12.0	11.0	11.0	10.0	8.0	0 to 12
Volume Change (%)		-7	-7	-7	-6	-6	-5	0 to -7
Shore A Hardness Change (%)								
Filterability	Denison TP	72	72	72	85	111	260	600 (max)
A-No Water (s) (Avg)	02100	98	98	98	105	124	271	2xA (max)
B-2% Water (s) (Avg)	HF-0							
Demulsibility, ML Oil/Water/Emulsion	Requirement	40/ 40/ 0 (<10 min)	40/ 40/ 0 (<10 min)	40/ 40/ 0 (<10 min)	40/ 40/ 0 (<10 min)	40/ 40/ 0 (<10 min)	40/ 40/ 0 (<10 Min)	40/37/3 (max) (30 minutes)
4-Ball Wear, 1h, 167°F, 1200 RPM, 40 kg	ASTM D-1401	0.4	0.4	0.4	0.4	0.4	0.4	USS 127 0.5 (max)
FZG Test A/8,3/90	ASTM D-4172	10	10	11	11	12	12+	10 (min)
	DIN 51354 Part 2							
Biodegradation Classification	ASTM D-5864	Ultimate PW1	Ultimate PW1	Ultimate PW1	Ultimate PW1	Ultimate PW1	Ultimate PW1	Ultimate PW1
Environmentally Friendly	OECD 301B ISO 15380	Readily yes	Readily yes	Readily yes	Readily yes	Readily yes	Readily yes	Readily meets/exceeds
USDA Biobased	New Carbon	>60%	>60%	>60%	>60%	>60%	>60%	meets/exceeds
Environmental Management System	ISO 14001:1996	yes	yes	yes	yes	yes	yes	meets/exceeds
Ecotoxicity LC-50 / EC-50	EPA 560/6-82-002, 003	meets/exceeds	meets/exceeds	meets/exceeds	meets/exceeds	meets/exceeds	meets/exceeds	meets/exceeds
<i>Note 1 Viscosity Sufficient for Application</i>								
<i>Note 2 Not Required</i>								
Product Item #		81460	81470	81310	81320	81330	81340	